

Almazora, October 10th, 2017

TEST	ASTM	Unit	FINISH			
			SATIN	SILK	PULIDO	RIVERWASHED
Moisture expansion	ASTM C370-12 (2016)	%	<0,1%	<0,1%	<0,1%	*PTR
Thermal expansion	ASTM C372-94 (2016)	(x10-6) °C-1	5,725	5,9	5,65	*PTR
Water absorption	ASTM C373-16	%	0,18%	0,20%	0,16%	*PTR
Crazing resistance	ASTM C424-93 (2016)	-	OK	OK	OK	*PTR
Thermal Shock resistance	ASTM C484-99 (2014)	-	OK	OK	OK	*PTR
Chemical resistance	ASTM C650-04 (2014)	-	OK	OK	OK	*PTR
Visible abrasion	ASTM C1027-09	Class	*PTR	Class 3	Class 5	*PTR
Deep abrasion	ASTM C1243-93 (2015)	mm <sup>3</sup>	102,5	*PTR	*PTR	*PTR
Stain resistance	ASTM C1378 (2014)	Class	*PTR	*PTR	*PTR	*PTR

\*PTR: Pending Test Results.  
This chart will be updated as we get more test results.